



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C08F 8/14, C09D 133/14	A1	(11) International Publication Number: WO 98/20052 (43) International Publication Date: 14 May 1998 (14.05.98)
<p>(21) International Application Number: PCT/EP97/06017</p> <p>(22) International Filing Date: 30 October 1997 (30.10.97)</p> <p>(30) Priority Data: 08/741,785 1 November 1996 (01.11.96) US</p> <p>(71) Applicant (for all designated States except PL): COOK COMPOSITES AND POLYMERS COMPANY [US/US]; 919 East 14th Avenue, North Kansas City, MO 64116 (US).</p> <p>(71) Applicant (for PL only): CRAY VALLEY S.A. [FR/FR]; Tour Total, 24, cours Michelet, F-92800 Puteaux (FR).</p> <p>(72) Inventors: CRUMP, Larry, Scott; 7404 North Park Avenue, Gladstone, MO 64118 (US). SUSPENE, Laurent, Gerard; Calle Rodriguez Arias, 69, 6° Drcha, E-48013 Bilbao Vizcaya (ES). KARR, Gregory, Scott; 2879 Road G5, Americus, KS 66835 (US). WILLIAMS, Kerry, R.; 235 S.W. Pinetree Lane, Lee's Summit, MO 64063 (US).</p> <p>(74) Agent: CHAILLOT, Geneviève; Cabinet Chaillot, 16-20, avenue de l'Agent Sarre, Boîte postale 74, F-92703 Colombes Cedex (FR).</p>		<p>(81) Designated States: BR, CA, CZ, HU, JP, KR, MX, PL, SG, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).</p> <p>Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i></p>
<p>(54) Title: NEW POLYMERS, PROCESS FOR MAKING THEM AND COATING COMPOSITIONS CONTAINING THEM, ESPECIALLY THERMOSETTING ACRYLIC GEL COAT COMPOSITIONS</p> <p>(57) Abstract</p> <p>An invention is disclosed which pertains to components for gel coat compositions, a process for making such gel coat compositions, and a process for making gel coated articles. Low molecular weight unsaturated polymers which incorporate multiple pendent and/or terminal acrylic or methacrylic vinyl groups are made by the addition polymerization of acrylate/methacrylate monomers with epoxy acrylates such as glycidyl methacrylate, followed by ring opening of the oxirane via action of a (meth)acrylic acid in combination with a ring-opening catalyst to produce the final unsaturated polymer. Gel coat compositions containing such polymers possess improved rheological properties and may be used to create durable in-mold coatings for articles requiring good hydrolytic stability and UV resistance.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav	TM	Turkmenistan
BF	Burkina Faso	GR	Greece		Republic of Macedonia	TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's	NZ	New Zealand		
CM	Cameroon		Republic of Korea	PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakhstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

NEW POLYMERS, PROCESS FOR MAKING THEM AND COATING
COMPOSITIONS CONTAINING THEM, ESPECIALLY THERMOSETTING
ACRYLIC GEL COAT COMPOSITIONS

The present invention relates to new polymers, to
5 a process for making them and to coating compositions
containing them, especially thermosetting acrylic gel coat
compositions.

This invention is especially in the field of gel
coat compositions, components for making gel coat
10 compositions, processes for making components for use in gel
coats, processes for making gel coat compositions for use in
making gel coated articles, processes for making gel coated
articles, and gel coated articles.

Durable polymeric coatings on composite materials
15 known as gel coats are well known. They are typically found
on composite materials that are exposed to the elements or
that require a smooth glossy finish. Examples of items
having gel coats include boat hulls, jet skis, pools, spas,
composite body panels on automobiles, vans and trucks, and
20 the like.

Such gel coats are often formed by applying a gel
coat composition to the inside of an open mold, applying the
composite article to the gel coat composition so that it is
in adhering contact with the gel coat composition, curing
25 the gel coat, and removing the gel coated article from the
mold. Gel coated articles can also be made by forming a
composite material in a multi-part mold, opening the mold
sufficiently to inject or apply a gel coat composition,
closing the mold, curing the gel coat, and removing the gel
30 coated article from the mold.

Gel coat compositions are known which comprise
oil-free unsaturated polyester condensation polymers in
mixtures of unsaturated reactive diluents, such as styrene,
which form crosslinked polymers by using a polymerization
35 initiator, such as a peroxide. A limitation of gel coats
made from unsaturated polyesters is that they typically have
less than desired hydrolytic stability and durability. The


hydrolytic instability can be attributed to polyol acidity and the presence of ester groups and the lack of exterior durability can be attributed to the presence of the aromatic component which is used as the reactive diluent.

5 Several approaches for addressing these limitations have been described in the prior art. These approaches include making polyester modifications and polyester alloys such as described in U.S. Patents 4,587,323 ; 5,118,783 ; and 5,376,460 and in SPI Composites
10 Institute Paper 17-H (1983) ; using epoxy chemistry such as described in U.S. Patents 4,367,192 and 5,389,443 and in SPI Composites Institute Paper 15-C (1991) ; urethane/urea chemistry such as described in U.S. Patents 3,928,299 ; 4,374,238 and 5,387,750 ; European Patent 254,232 ; and
15 Plastics Technology, Vol. 34, No. 3, March 1988, page 13 ; and acrylic chemistry as described in U.S. Patents 4,177,338 ; 4,742,121 ; and 5,045,613.

While these approaches have led to improvements in hydrolytic stability and durability, room exists for further
20 improvements in these characteristics. In addition, improvements are still needed in gel coat composition rheology. The desirable gel coat composition rheology has a high thixotropic ratio to allow for ease of application to the mold while preventing sagging or running after it is
25 applied, particularly in open mold coating processes.


These and other desirable objectives are achieved by gel coat compositions, components for making gel coat compositions, processes for making a gel coat composition for use in making gel coated articles, processes for making
30 gel coated articles and gel coated articles of the present invention.

One aspect of the present invention is a polymer for making coating compositions, and especially gel coat compositions, represented by the formula :



wherein :

- X is a divalent saturated aliphatic group having a pendant ester group without any polymerizable double bonds ;
- Y is a divalent saturated aliphatic group having a pendant group of formula :




in which R^1 is a divalent, aliphatic, saturated, hydroxyl-containing group and R^2 is a hydrocarbyl group with at least one polymerizable carbon-carbon double bond ;

- W is an end group derived from a mercaptan of the general formula R^3-SH in which R^3 is a hydrocarbyl group having 2 to 20 carbon atoms and not having a polymerizable carbon-carbon double bond ;
- m is a number in the range from 1 to 10 ;
- n is a number in the range from 1 to 50 ;
- n/m is in the range from about 1 to 5 ;

and the polymer has a number average molecular weight of at least 2,500.

Another aspect of this invention is a process for making a polymer for use in a coating composition, especially a gel coat composition comprising :


(a) copolymerizing at least one monomer of the formula :



in which

- R^4 is a hydrogen atom or a saturated aliphatic group of 1 to 8 carbon atoms and
- R^5 is a saturated aliphatic group of 1 to 18 carbon atoms

with at least one monomer of the formula :




in which :

- R^6 is a hydrogen atom or a saturated aliphatic group of 1 to 8 carbon atoms,
- R^1 represents a divalent, aliphatic, saturated, hydroxyl-containing group having at least one carbon atom,

the molar ratio of the compound of formula (II) to the compound of formula (III) being in the range from about 1:1 to about 5:1 ;

in the presence of a polymerization initiator, and of a polymer chain terminating compound of the formula :



in which :

- R^3 is a hydrocarbyl group having 2 to 20 carbon atoms and not having a polymerizable carbon-carbon double bond,

such that the polymer produced will have a number average molecular weight of at least 2,500 ; and

(b) reacting the product of step (a) in an oxirane ring-opening reaction with at least one monomer of the formula :



in which R^7 is either -H or -CH₃.

Another aspect of the present invention is a coating composition curable by a free radical initiator system and comprising at least one polymer as described above. According to one embodiment, said free radical initiator system comprises a photo-initiator.

Yet another aspect of this invention is a gel coat composition comprising :

- (a) at least one polymer for making a gel coat composition described above and
- (b) a rheology synergist concentrate.

An embodiment of said rheology synergist concentrate is described hereinbelow.

Yet another aspect of this invention is a process for making a gel coat comprising :

- 5 (a) dispersing in the polymer described above a rheology synergist concentrate, a free radical initiator and, optionally, a filler ; and
- (b) adding as needed an acrylic monomer until a predetermined viscosity is obtained.

10 Another aspect of this invention is a rheology synergist concentrate for making a gel coat composition comprising :

- (a) at least one thixotrope ;
- (b) at least one aliphatic alcohol having from 1 to 20
15 carbon atoms and 1 to 3 hydroxy groups ; and
- (c) at least one alkali metal salt of an organic acid.

Yet another aspect of this invention is a process for making a gel coated article comprising :

- (a) applying to a mold the gel coat composition described
20 above ;
- (b) partially curing the gel coat of step (a), for example during a time period less than or equal to two hours, said curing being advantageously facilitated by adding a co-initiator compound, such as t-butyl peroctoate and
25 2,5-dimethyl-2,5-di(2,5-diethylhexanoyl peroxy)hexane ;
- (c) applying to the exposed surface of the gel coat of step (b) an article having a shape corresponding to the shape of the gel coat in the mold, to form a laminate ;
- (d) allowing the laminate of step (c) to further cure to
30 form the gel coated article ; and
- (e) removing the gel coated article of step (d) from the mold.

Another aspect of this invention is the gel coated article obtainable from the polymers, compositions, and
35 processes of the present invention described above.

BRIEF DESCRIPTION OF THE DRAWING

- FIG 1 shows a diagram illustrating the abusive spray test, which is described in more detail below.

DETAILED DESCRIPTION OF THE INVENTION

5 The polymers according to this invention may be represented by formula (I) :



In that formula, X is a divalent saturated
10 aliphatic group having a pendant ester group without any polymerizable carbon-carbon double bonds. Preferably, X is substituted or unsubstituted ethylene and may, for example, be represented by the formula :




wherein R^8 is a pendant ester group, preferably $-\text{C}(\text{O})-\text{O}-\text{R}^9$
20 in which R^9 is an aliphatic group having from 1 to 20, more preferably 1 to 12, and even more preferably 1 to 8, carbon atoms.


Y is a divalent saturated aliphatic group having a pendant group of the formula (IA). Preferably, Y is
25 substituted or unsubstituted ethylene, and may, for example, be represented by the general formula :




Z is a group of the formula :



in which R^1 is a divalent, aliphatic, saturated, hydroxyl-containing group. In a preferred embodiment, R^1 is represented by the formula :



5 or



R^2 is preferably an aliphatic group having from 2
10 to 20 carbon atoms, more preferably from 2 to 8 carbon atoms, and even more preferably from 2 to 4 carbon atoms, and at least one polymerizable carbon-carbon double bond, preferably just one polymerizable carbon-carbon double bond.

W is an end group derived from a mercaptan of the
15 general formula $R^3\text{-SH}$ in which R^3 is a hydrocarbyl group having at least 2, more preferably at least 10, carbon atoms up to 20, preferably up to 14, carbon atoms, such as a substituted or unsubstituted alkyl group. R^3 may bear a functional group such as OH. Examples of mercaptans $R^3\text{SH}$
20 are n-butyl mercaptan, n-octyl mercaptan, n-dodecyl mercaptan, n-tert.-dodecyl mercaptan and 2-mercaptoethanol.

The number of Y units, m, is a number in the range from at least about 1 to about 10, preferably in the range from at least about 1 to about 5. The number of X units, n,
25 is a number in the range from at least about 1 to about 50, preferably in the range from at least about 1 to about 10. The n/m ratio is a number in the range from about 1, preferably at least about 1.50, more preferably at least about 2, to about 5, preferably up to about 4, and more
30 preferably up to about 3.

The first step in making the polymer of this invention is to make a saturated acrylic polymer by the polymerization of an acrylic monomer with an epoxy acrylate. Examples of acrylic monomers include methyl methacrylate,
35 lauryl methacrylate, butyl methacrylate, etc. Examples of epoxy acrylates include glycidyl methacrylate and glycidyl

acrylate. Polymerization is generally initiated using a chemical polymerization initiator. A non-peroxide initiator containing an azo group, such as 2,2 azobis (2,4-dimethylvaleronitrile), is preferred. The amount of
5 initiator is preferably in the range from 0.1 to 1 part by volume. The polymer chains are terminated by reacting them with a mercaptan which does not have any polymerizable carbon-carbon double bonds. The mercaptan is added in an amount which is preferably in the range from 0.5 to 5 parts
10 by volume.

The second step in making the polymer of this invention is to make an unsaturated acrylic polymer from the above saturated acrylic polymer by reacting a (meth)acrylic acid with the epoxy functional groups on the saturated
15 acrylic polymer by using a ring opening catalyst such as triphenylphosphine, etc. The resulting polymer has a number average molecular weight in the range from 900 to 3,000.

Lastly, an acrylic monomer is added until the solution has reached a predetermined viscosity, which is
20 preferably less than 1000 centipoise as measured by Brookfield viscometer at 25°C (77°F).

The resulting polymer can be further crosslinked with various crosslinking agents, such as monofunctional and multifunctional methacrylates and acrylates, as well as
25 other monomers, oligomers, and polymers capable of participating in free-radical addition polymerizations such as styrene, vinyl toluene, alpha methyl styrene, etc.

As indicated above, the polymers of this invention are useful for making coating compositions, particularly gel
30 coat compositions. The gel coat composition of the present invention is comprised of at least one polymer as described above combined with a rheology synergist concentrate.

The rheology synergist concentrate is comprised of at least one thixotrope, at least one aliphatic hydroxide
35 having from 1 to 20 carbon atoms and 1 to 3 hydroxy groups, and at least one alkali metal salt of an organic acid.

Preferred thixotropes in the gel coat compositions according to this invention include silica, such as fumed silica and precipitated silica, silica gels, and bentonite clays. The thixotrope is preferably present in an amount of
5 at least about 1 wt%, more preferably at least about 1.5 wt%, and even more preferably at least about 1.8 wt%, up to about 5 wt%, more preferably up to 2.5 wt%, and even more preferably up to 2.2 wt%, based on the total weight of the gel coat composition.

10 Preferred aliphatic hydroxides in the gel coat compositions according to this invention are polyols including glycols, such as ethylene glycol, propylene glycol, etc., and glycerol, sorbitol, ethoxylated sorbitol, etc. The aliphatic hydroxide is preferably present in an
15 amount of at least about 0.2 wt%, more preferably at least about 0.3 wt%, up to about 1.0 wt%.

Preferred alkali metal salts of organic acids in the gel coat compositions according to this invention include salts in which the alkali metal is Li^+ , K^+ , and/or
20 Na^+ . The organic acid from which the salt is derived may be a carboxylic acid having from 6 to 10 carbon atoms, such as hexanoic acid, octanoic acid, neodecanoic acid, etc. Specific examples include potassium octoate, which is available from Mooney Chemical Company under the trademark
25 HexchemTM, calcium octoate, which is available from Huls America under the trademark NuxtraTM, etc. The alkali metal salt is preferably present in an amount of at least about 200 ppm, more preferably at least about 250 ppm, and even more preferably at least about 280 ppm, up to about 800 ppm,
30 more preferably up to about 400 ppm, and even more preferably up to about 320 ppm.

The combination of the aliphatic hydroxide and the alkali metal salt of an organic acid is referred to herein as a synergist package. When they are added in combination,
35 the ratio of aliphatic hydroxide to alkali metal salt is preferably in the range from 1:1 to 3:1, more preferably from 1.5:1 to 2.5:1. For example, a preferred weight ratio

of sorbitan monolaurate to Potassium HexchemTM is about 2 to 1. The synergist package is preferably present in an amount of at least about 0.3 wt% up to about 1.0 wt%, based on the weight of gel coat composition.

5 Other additives, such as fillers, thixotropic agents, rheological control additives, UV absorbers, solvents and the like, can be incorporated into the coating composition as desired.

 Examples of fillers include clay, magnesium oxide,
10 magnesium hydroxide, calcium carbonate, calcium silicate, mica, aluminum hydroxide, barium sulfate, talc, etc. Fillers are defined herein as not including the thixotropes as defined above, as well as coloring pigments. Preferred amounts of filler are in the range from 5 to 30 wt%.

15 In a preferred embodiment, the gel coat may be made by high speed dispersion of thixotrope and fillers into the above resin solution. A synergist package is then added. A free radical initiator is then added which will facilitate the formation of free radicals necessary for
20 curing the gel coat composition. Lastly, an acrylic monomer is added to the gel coat composition until the desired viscosity is obtained.

 In one embodiment of this invention, the free radical initiator is a photoinitiator, and the gel coat
25 composition is cured by UV radiation. These include photoinitiators such as benzophenone, acetophenone and its derivatives, benzoin, benzoin ethers, thioxanthenes, halogenated compounds, oximes, and acyl phosphine oxides. Preferred are those photoinitiators which do not strongly
30 discolor when exposed to sunlight, e.g. the acyl phosphine oxides and 2-hydroxy-2-methyl-1-phenylpropan-1-one.

 In another embodiment of the gel coat composition of the invention, a thermally activated cure system is employed, such as a system comprising a metal catalyst, a
35 polyallylic initiator, such as SANTOLINK XI-100 from Monsanto, and, optionally, a nonpolyallylic peroxide initiator. In a preferred embodiment of this invention, the

thermally activated free radical initiator is an oxidation/reduction system. The oxidation/reduction system comprises a metal catalyst and any combination of one or more compounds selected from the following : amines, alkyl
5 acetoacetates, alkyl acetoacetamides, and alkyl and aryl acetanilides. The gel coat composition may be cured by heat (typically induced by infrared (IR) radiation).

The metal catalyst is any metallic salt that will promote or accelerate the rate of cure of the gel coat
10 composition. Typically, these catalysts are salts of metals and organic acids. Representative metals are cobalt, manganese, vanadium, potassium, zinc and copper. The metal catalyst includes, among others, a variety of metal driers. Preferred metallic salt driers include the octoates,
15 naphthenates and neodecanoates of cobalt, manganese, vanadium, potassium, zinc and copper. An especially preferred catalyst is cobalt octoate solution in an amount preferably in the range from about 0.012 to 0.036 wt% of cobalt (e.g., 0.1 to 0.3 wt% of a 12% cobalt octoate
20 solution may be used).

The oxidation/reduction system also contains any combination of one or more compounds selected from the following : amines, alkyl acetoacetates, alkyl
acetoacetamides, and alkyl and aryl acetanilides. For
25 example, dimethyl aniline is added in an amount preferably in the range from 0 to 0.4 wt%, more preferably 0.1 to 0.4 wt%. Dimethyl acetoacetate and/or ethyl acetoacetate and/or methyl acetoacetate and/or acetoacetanilide, etc. may be added preferably, in an amount ranging from 0 to 0.2 wt%,
30 more preferably 0.05 to 0.15 wt%, to the oxidation/reduction system.

In a preferred embodiment of this invention, a peroxide based co-initiator is used, more preferably in conjunction with the oxidation/reduction system, to cure the
35 gel coat and the laminating resin. These co-initiators are typically non-polyallylic peroxides. They include any of the common peroxides such as benzoyl peroxide ; dialkyl or

aralkyl peroxides such as di-t-butyl peroxide, dicumyl peroxide, cumylbutyl peroxide, 1,1-di-t-butyl-peroxy-3,5,5-trimethylcyclohexane, 2,5-dimethyl-2,5-di-t-butylperoxy hexane and bis(alpha-t-butylperoxy isopropylbenzene) ;
5 dialkanoyl peroxides such as 2,5-dimethyl-2,5-di(2,5-diethylhexanoyl peroxy)hexane ; peroxyesters such as t-butylperoxy pivalate, t-butyl peroctoate, t-butyl perbenzoate, 2,5-dimethylhexyl-2,5-di(perbenzoate), dialkylperoxymonocarbonates and peroxydicarbonates ;
10 hydroperoxides such as t-butyl hydroperoxide, p-methane hydroperoxide, pentane hydroperoxide and cumene hydroperoxide ; and ketone peroxides such as cyclohexanone peroxide and methyl ethyl ketone peroxide. Typically, a methyl ethyl ketone peroxide (MEKP) co-initiator is used
15 which consists of a solution blend of various peroxides and hydroperoxides, including monomer MEKP, dimer MEKP, cyclic trimer MEKP, and hydrogen peroxide, in an inert carrier such as dibutyl phthalate.

Preferably, the co-initiator is t-butyl peroctoate
20 (tBP), available from Atochem, a division of Elf Aquitaine, under the trademark Lupersol 256, or 2,5-dimethyl-2,5-di(2,5-diethylhexanoyl peroxy)hexane, available from Akzo under the trademark Trigonox 141. Gel coat of Example 1B below according to this invention cures 47% to completion
25 isothermally when cured with 2,0% MEKP initiator. The inventors have found that the same gel coat cures 82% to completion isothermally when cured with 1,5% tBP initiator. In general, the time period necessary for curing is less than or equal to two hours when using a tBP or 2,5-dimethyl-
30 2,5-di(2,5-diethylhexanoyl peroxy)hexane initiator.

Preferably, the concentration of the co-initiator solution ranges from about 1 wt% to about 2.5 wt%, preferably from about 1.2 wt% to about 2 wt%.

Other methods of curing the gel coat are possible
35 and will be apparent to one skilled in the art.

The gel coating process is well known in the art. The gel coat composition is applied to the surface of a mold

and allowed to partially cure. If the gel coat composition contains a photoinitiator as the free radical initiator, then the gel coat composition is exposed to radiation having the appropriate wavelength and intensity to activate the photoinitiator. If the gel coat composition contains a thermally activated free radical initiator, then the gel coat composition is exposed to heat, preferably in the form of IR radiation. The partially cured gel coat composition is relatively soft, possibly even tacky.

10 An article to be gel coated is applied to the partially cured gel coat composition to form a laminate and the laminate undergoes a second stage cure. This second stage cure may be carried out by heating the mold to an elevated temperature or by other means, such as irradiation. 15 Afterwards, the gel coated article is removed from the mold. The gel coat becomes an integral part of the finished laminate and is usually used to improve surface appearance. This process is described in more detail in Lubin, Handbook of Composites p. 764, Van Nostrand Reinhold Company (1982), 20 which is incorporated herein by reference.

The article to be gel coated may be a fully or partially cured polymer resin or composite of reinforcing material in a polymer resin matrix. The reinforcing material may be selected from any conventionally used in the composite plastics industry, such as glass fiber, 25 polyethylene fiber, carbon fiber, metal fiber, ceramic fiber, etc., and the resin may be selected from a wide range of resins, such as polyester resins, epoxy resins, polyester carbonate resins, polycarbonate resins, polystyrene resins, 30 polymethylmethacrylate resins, etc. The mold surface preferably corresponds to the shape of the article in negative relief. It may be an open mold or a matched mold.

The examples which follow are illustrative of the present invention. They are not to be taken as limiting the 35 scope of the claimed invention. Unless stated otherwise, all percents and ratios of amounts are by weight.

EXAMPLESDescription of Testing MethodsPanel Preparation

t-butyl peroxoate (tBP) (1.5 wt%) is added to the
5 gel coat and stirred for 1 minute. The gel coat is then
sprayed onto a waxed and buffed flat tempered glass plate to
a thickness of 0.381 - 1.016 mm (15-40 MILS). After curing
for 1-2 hours, a 3.175 mm (1/8") laminate is made using
10 chopped fiberglass and a polyester resin (40% mat/60%
resin). A methyl ethyl ketone peroxide (MEKP) co-initiator
at 1.2 wt% is used to cure the polyester resin. The
laminate is allowed to cure for 16-20 hours, then removed
from the mold and cut into test parts.

Boiling Water Resistance

15 A 17.78 cm x 17.78 cm (7" x 7") part from the
above panel is connected to a boiling water tank, using
deionized water, (ANSI Z124) and exposed for 100 hours. The
exposed panels are then rated on a scale of 0-5 blisters,
color change, change in fiber prominence, cracks, and loss
20 of visible gloss with 0 = no change, and 5 = maximum change.

QUV Weathering

Test panels are also subjected to the weathering
test procedure (ASTM 53, incorporated herein by reference)
using the cycle of 4 hours condensation at 40°C, followed by
25 4 hours exposure at 60°C to a UV bulb with at peak energy of
340 nm. Test panels are inspected at 500 hour intervals.

Rheology, Brookfield Viscometer

The thixotropy of the gel coat is determined by
use of a Brookfield Viscometer. An 8 oz. jar of gel coat at
30 25°C (77°F) is used as a test sample. Using a #4 spindle on
the viscometer the viscosity is measured at 2 and 20 rpm.

The thixotropic index is calculated as the ratio of the viscosity at 2 rpm to the viscosity at 20 rpm.

Cure Testing, DSC

The percent cure of a gel coat achieved by the free radical initiator is measured by differential scanning calorimetry (DSC). A sample of the gel coat is cured with the free radical initiator and the isothermal cure energy of the crosslinking reaction is measured by DSC under isothermal conditions, (30°C). The sample's residual cure is measured by a temperature ramp test which consists of ramping the DSC cell temperature to 250 C after a 3 hour cure time or when the exotherm has stopped. The percent cure is then determined by dividing the isothermal cure energy by the total cure energy, the total cure energy being equal to the isothermal cure energy plus the residual cure energy determined from the temperature ramp test.

Pigment Dispersions, Roll Mill

Pigment dispersions in an acrylic resin are made with a three roll mill. The pigments are milled until a 7 Hegman grind is achieved.

Abusive Spray Test on Pigment Dispersions

The following is the test procedure for an Abusive Spray Test :

- 1) Wax and buff and glass mold.
- 25 2) Make a tape line near the bottom of the mold with 2.54 cm (1") tape.
- 3) Cover half of the upper portion of the mold with 7.62 cm (3") tape.
- 4) Weigh 100 g and 200 g samples of gel coat.
- 30 5) Mix the 100 g sample in the correct proportion with the co-initiator as specified.

- 6) Use part of this sample to make a draw-down with a 0.5842 mm (0.023") gap in the lower section of the mold, below the 2.54 cm (1") line.
- 7) With the remainder of the this sample, make overspray
5 at 2.4131 bar (35 psi) static pressure and 1.0342 bar (15 psi) pot pressure. (Static pressure refers to the air pressure directed into the liquid coating streamer at the spray tip of the spray gun. This variable is used to regulate the degree of fluid atomization. Pot
10 pressure refers to the air pressure applied to surface of the liquid coating in the container (pot) which holds the coating prior the spray. This pressure forces the liquid through a suction tube and continuing to the spray tip. The level of pot pressure is used to
15 regulate the flow rate of the coating through the spray gun.)
- 8) Pull 7.62 cm (3") tape
- 9) Wait a time interval equal the gel time of this sample, then mix the 200 g sample in the correct proportion
20 with the co-initiator as specified.
- 10) Adjust the spray gun to 3.8610 bar (56 psi) static pressure and 1.0342 bar (15 psi) pot pressure.
- 11) Spray 0.4572 - 0.5588 mm (18-22 MILS) over the entire mold using 3 passes.
- 25 12) Pull the 2.54 cm (1") tape.
- 13) Pour the remainder of the 200 g sample onto the mold such that the pourdown is centered over the line which divided the overspray and nonoverspray sections.
- 14) Place the mold in a vertical position.
- 30 15) After the film has gelled, place mold in a 66°C (150°F) oven for 30-40 minutes.
- 16) Remove the mold from oven, let cool, tape then de-mold.

Figure 1 shows a diagram illustrating the abusive spray test. Figure 1 shows a mold 1 having a spray area 2, 35 overspray area 3, tapeline sag area 4, drawdown area 5 and typical pour down area 6.

COMPARATIVE EXAMPLE 1A. Preparation of a Conventional Orthophthalic Neopentyl Glycol Unsaturated Polyester Resin

In a reactor equipped with a stirrer, thermometer,
 5 a water separating column fitted with a reflux condenser,
 and a nitrogen inlet, the following ingredients are added.

	<u>Components</u>	<u>Grams</u>
	Neopentyl Glycol	1840
	Propylene Glycol	1042
10	Phthalic Anhydride	2024
	Maleic Anhydride	1594

The charged mixture is heated to reflux and a
 total of 539 parts of water are distilled off. The reaction
 mixture is held at 220°C until an acid number of 15-20 is
 15 obtained. The reaction mixture is then cooled to less than
 140°C and the following ingredients are added.

	<u>Components</u>	<u>Grams</u>
	Methoxyhydroquinone	0.9
	Styrene	3500

20 B. Preparation of a Conventional Gel Coat

A gel coat is prepared by blending the following
 ingredients :

	<u>Components</u>	<u>Grams</u>
	Resin solution from Part A above	42.30
25	12% Cobalt drier	0.14
	15% Potassium Hexchem 97	0.20
	Amorphous-Fumed Silica	1.06
	Amorphous-Silica	1.27
	Magnesium Silicate	8.46
30	Calcium Carbonate	8.46
	Titanium Dioxide	10.58
	Styrene	15.44

Methyl Alcohol	0.74
Sorbitan Monolaurate	0.42

The resulting coating can then be cured by adding a 2.0 wt% MEKP co-initiator and spraying the coating on a glass mold as described in the Test Panel Preparation.

EXAMPLE 1

A. Preparation of an Acrylic Polymer According to the Present Invention

A reactor equipped with a stirrer, thermometer, total condenser, and nitrogen sparge inlet is charged with 4906 grams of methyl isobutyl ketone. The solvent is heated to 90°C (194°F) and the following two mixtures of components are added to the reactor, dropwise and separately, over a two hour period :

15

MIXTURE 1

<u>Components</u>	<u>Grams</u>
Glycidyl Methacrylate	1248
Butyl acrylate	2248
Lauryl Methacrylate	3468
2-Mercaptoethanol	20

20

MIXTURE 2

<u>Components</u>	<u>Grams</u>
2,2-azobis(2,4-dimethylvaleronitrile)	216
Methyl Isobutyl Ketone	1224

25

The reaction is held at 90°C (194°F) for two hours after the addition period. Once the hold period is complete, the reactor is set to recover solvent and heated to 149°C (300°F). At 149°C (300°F), a vacuum of 846.62 millibars (25 inches of Hg) is pulled until no more

solvent leaves the reactor. The resulting polymer is cooled to 88°C-93°C (190-200°F).

Once the reaction temperature has reached 88-93°C (190-200°F), the reactor's atmosphere is changed from nitrogen to oxygen and 1 gram of 4-methoxyphenol is added. The following ingredients are mixed together, making sure all solids are dissolved. Then this mixture is added to the reactor.

	<u>Components</u>	<u>Grams</u>
10	Triphenylstilbine	60
	Triphenylphosphine	20
	Methacrylic Acid	720

This reaction is exothermic and the reactor temperature must be kept below 110°C (230°F). Once the exotherm subsides, the reaction is held at 96.1-101.7°C (205-215°F) until an acid number of less than 5 and epoxide equivalent weight of greater than 8000 is obtained.

The resultant polymer is then cooled to 93°C (200°F) and reduced to 67 wt% solids with 1,4-butanediol dimethacrylate.

B - Preparation of an Acrylic Gel According to the Present Invention

A gel coat is prepared by blending the following ingredients :

	<u>Components</u>	<u>Grams</u>
25	Acrylic Resin Solution from Part A Above ...	54.50
	Titanium Dioxide	19.0
	Amorphous-Fumed Silica	2.0
	Magnesium Silicate	5.0
30	Sorbitan Monolaurate	0.20
	12% Cobalt drier	0.15
	15% Potassium Hexchem 97	0.20
	Ethylene Glycol	0.20

2,4-Pentanedione	0.10
Dimethylparatoluidine	0.20
Methyl Methacrylate	18.50
Paraffin Wax	0.20

5 QUV Weathering Comparison Between Gel Coats in Comparative Example 1B and Example 1B of the Present Invention

	Gel Coat	Hours	dE	% Gloss
	Comparative Example 1B	500	3.19	82.0
		3000	7.14	17.5
10	Example 1B of the Present Invention	500	1.14	97.3
		3000	1.26	92.2

Boil Test Comparison Between Gel Coats in Comparative Example 1B and Example 1B of the Present Invention

	Gel Coat	Comparative Example 1B	Exemple 1B of the Present Invention
	Blisters	4.47	2.75
15	Color Change	1.60	0.69
	Fiber Prominence	0.47	1.67
	Cracks	1.23	1.08
	Loss of Gloss	0.4	0.00
	Total	8.17	6.19

20

Rheology, Brookfield Viscometer

Viscosity measurements obtained using a Brookfield viscometer of a gel coat similar to Comparative Example 1B are as follows :

RPM	Viscosity (cps)
2	35,750
20	5,500
Thixotropic Index	6.50

- 5 Viscosity measurements obtained using a Brookfield viscometer of a gel coat similar to Example 1B without the synergist package are as follows :

10

RPM	Viscosity (cps)
2	150
20	150
Thixotropic Index	1.00

Viscosity measurements obtained using a Brookfield viscometer of a gel coat similar to Example 1B with the synergist package are as follows :

15

RPM	Viscosity (cps)
2	26,000
20	4,050
Thixotropic Index	6.40

Cure Testing, DSC

- 20 A gel coat similar to Comparative Example 1B cures 75% to completion isothermally when cured with 2.0% MEKP co-initiator. A gel coat similar to Example 1B of the present invention cures 47% to completion isothermally when cured with 2.0% MEKP co-initiator. The same gel coat (Example 1B)
- 25 when cured with 1.5% tBP co-initiator, cures 82% to completion isothermally. In general, the time period is less than or equal to two hours when using a tBP co-initiator.

EXAMPLE 2

An unsaturated polyester (PE) pigment dispersion resin was added to a gel coat similar to Example 1B. The QUV weathering test and a boiling water test was performed on panels both with and without the unsaturated polyester pigment dispersion resin added.

<u>Components</u>	<u>Grams</u>
Example 1B	93.0
Unsaturated Polyester Resin	7.0

10 QUV Weathering Comparison Between Gel Coats

Gel Coat Retention	Hours	dE	% Gloss
With PE Resin	500	1.19	97.1
	3000	1.43	54.4
Without PE Resin	500	1.12	97.4
	3000	1.77	73.3

15 Boil Test Comparison Between Gel Coats

20

Gel Coat	With PE Resin	Without PE Resin
Blisters	2.75	2.75
Color Change	1.92	0.61
Fiber Prominence	0.86	0.69
Cracks	1.50	0.05
Loss of Gloss	0.00	0.00
Total	7.03	4.10

EXAMPLE 3

25 A. Preparation of an Acrylic Pigment Dispersion Resin

A reactor equipped with a stirrer, thermometer, total condenser, and nitrogen sparge inlet was charged with

4906 grams of isopropanol. The solvent is heated to 90°C (194°F) and the following two mixtures of components are added to the reactor, dropwise and separately, over a two hour time period :

5

MIXTURE 1

<u>Components</u>	<u>Grams</u>
Glycidyl Methacrylate	1696
Butyl Acrylate	4581
Lauryl Methacrylate	2863

10

MIXTURE 2

<u>Components</u>	<u>Grams</u>
2,2-Azobis(2,4-dimethylvaleronitrile)	216
Isopropanol	1223

The reaction is held at 90°C (194°F) for two hours after the addition time period. Once the hold period is complete, the reactor is set to recover solvent and heated to 149°C (300°F). At 149°C (300°F), a vacuum of 846.62 millibars (25 inches of Hg) is pulled until no more solvent leaves the reactor. The resulting polymer is cooled to 88-93°C (190-200°F).

Once the reaction temperature has reached 88-93°C (190-200°F), the reactor's atmosphere is changed from nitrogen to oxygen and 1 gram of 4-methoxyphenol is added. The following ingredients are mixed together, making sure all solids are dissolved. Then this mixture is added to the reactor.

<u>Components</u>	<u>Grams</u>
Triphenylstilbine	60
Triphenylphosphine	20
Acrylic Acid	859

This reaction is exothermic, and the reactor temperature must be kept below 110°C (230°F). Once the

exotherm subsides, the reaction is held at 96.1-101.7°C (205-215°F) until an acid number of less than 5 and an epoxide equivalent weight of greater than 8000 is obtained.

5 B - Preparation of a Gel Coat Containing the Acrylic Dispersion Resin

The acrylic pigment dispersion resin obtained in Part A above was added to a gel coat using a procedure similar to that used in Example 1B. QUV weathering test and a boiling water test was run on a panel with and without the acrylic pigment dispersion resin added.

<u>Components</u>	<u>Grams</u>
Example 1B Gel Coat	93.0
Acrylic Pigment Dispersion Resin	7.0

QUV Weathering Comparison Between Gel Coats

15	Gel Coat Retention	Hours	dE	% Gloss
	With Acrylic Resin	500	1.85	94.4
		2500	1.69	94.2
	Without Acrylic Resin	500	1.42	95.7
		2500	1.46	93.8

Boil Test Comparison Between Gel Coats

	Gel Coat	With Acrylic Resin	Without Acrylic Resin
20	Blisters	2.67	2.92
	Color Change	1.42	1.5
	Fiber Prominence	0.58	0.92
	Cracks	1.50	0.93
	Loss of Gloss	0.00	0.00
25	Total	6.17	6.27

EXAMPLE 4A. Preparation of Acrylic Pigment Dispersions

Orange and white pigment dispersions were made using a three roll mill. The dispersions were made in an acrylic resin similar to Example 3A using the following ingredients.

	<u>White Dispersion</u>	<u>Grams</u>
	Example 3A Resin	50
	Titanium Dioxide	50
10	<u>Orange Dispersion</u>	<u>Grams</u>
	Example 3A Resin	75
	Mono-azo Orange	25

B - Preparation of an Orange Gel Coat

An orange gel coat was made using the pigment dispersion in Part A above and a neutral gel coat similar to Example 4 only without the titanium dioxide.


	<u>Orange Gel Coat</u>	<u>Grams</u>
20	Example 1B Gel Coat Base (w/o TiO ₂)	86.9
	White Dispersion	2.1
	Orange Dispersion	11.0

An abusive spray test performed on the orange gel coat above showed little pigment flocculation or separation.

Although the process of this invention has been described in considerable detail by the preceding examples, this detail is for the purpose of illustration only and is not to be construed as a limitation on the spirit and scope of the invention as described in the appended claims.

CLAIMS


1 - A polymer represented by the formula :



5

wherein :

- X is a divalent saturated aliphatic group having a pendant ester group without any polymerizable double bonds ;
- 10 - Y is a divalent saturated aliphatic group having a pendant group of formula :



15

in which R^1 is a divalent, aliphatic, saturated, hydroxyl-containing group and R^2 is a hydrocarbyl group with at least one polymerizable carbon-carbon double bond ;

20

- W is an end group derived from a mercaptan of the general formula R^3-SH in which R^3 is a hydrocarbyl group having 2 to 20 carbon atoms and not having a polymerizable carbon-carbon double bond ;
- m is a number in the range from 1 to 10 ;
- n is a number in the range from 1 to 50 ;
- n/m is in the range from about 1 to 5 ;

and the polymer has a number average molecular weight of at least 2,500.

25

2 - The polymer of Claim 1 wherein X is an ethylene group having a pendant group represented by the formula $-C(O)-O-R^9$ in which R^9 is an aliphatic group having from 1 to 20 carbon atoms.

30

3 - The polymer of Claim 1 wherein n/m is in the range from about 1 to 4.

4 - The polymer of Claim 2 wherein n/m is in the range from about 1 to 4.


5 - The polymer of Claim 1 wherein n/m is at least 1.50.

35

6 - The polymer of Claim 2 wherein n/m is at least 1.50.

7 - A process for making a polymer comprising :


(a) copolymerizing at least one monomer of the formula :



in which

- 10 - R^4 is a hydrogen atom or a saturated aliphatic group of 1 to 8 carbon atoms and
 - R^5 is a saturated aliphatic group of 1 to 18 carbon atoms

with at least one monomer of the formula :




in which :

- 20 - R^6 is a hydrogen atom or a saturated aliphatic group of 1 to 8 carbon atoms,
 - R^1 represents a divalent, aliphatic, saturated, hydroxyl-containing group having at least one carbon atom,

25 the molar ratio of the compound of formula (II) to the compound of formula (III) being in the range from about 1:1 to about 5:1 ;

in the presence of a polymerization initiator, and of a polymer chain terminating compound of the formula :




in which :

- R^3 is a hydrocarbyl group having 2 to 20 carbon atoms and not having a polymerizable carbon-carbon double bond,

such that the polymer produced will have a number average molecular weight of at least 2,500 ; and

- 5 (b) reacting the product of step (a) in an oxirane ring-opening reaction with at least one monomer of the formula :



- 10 in which R^7 is either -H or $-\text{CH}_3$.

8 - The process for making a polymer according to Claim 7, wherein the polymerization initiator is a non-peroxide initiator.

- 15 9 - A coating composition curable by a free radical initiator system and comprising at least one polymer according to Claim 1.

10 - The coating composition according to claim 9, wherein said free radical initiator system comprises a photoinitiator.

- 20 11 - A gel coat composition comprising :

- (a) at least one polymer according to Claim 1 ; and
(b) a rheology synergist concentrate.

12 - A gel coat composition according to Claim 11, wherein the rheology synergist concentrate comprises :

- 25 (i) at least one thixotrope ;
(ii) at least one aliphatic alcohol having from 1 to 20 carbon atoms and 1 to 3 hydroxy groups ; and
(iii) at least one alkali metal salt of an organic acid.

- 30 13 - A process for making a gel coat composition comprising :

- (a) dispersing into the polymer according to Claim 1 a rheology synergist concentrate, a free radical initiator and
35 (b) adding as needed an acrylic monomer until a predetermined viscosity is obtained.

14 - The process for making a gel coat composition according to Claim 11 wherein step (a) further comprises dispersing a filler into the polymer.

15 - A rheology synergist concentrate comprising :

- 5 (a) at least one thixotrope ;
(b) at least one aliphatic alcohol having from 1 to 20 carbon atoms and 1 to 3 hydroxy groups ; and
(c) at least one alkali metal salt of an organic acid.

10 16 - A process for making a gel coated article comprising :

- (a) applying to a mold a gel coat composition according to Claim 11 ;
(b) partially curing the gel coat composition of step (a) ;
(c) applying to the exposed surface of the gel coat of step
15 (b) an article having a shape corresponding to the shape of the gel coat in the mold, to form a laminate ;
(d) allowing the laminate of step (c) to further cure to form the gel coated article ; and
(e) removing the gel coated article of step (d) from the
20 mold.

17 - The process of Claim 16 wherein the time period for step (b) is less than or equal to two hours.

18 - The process of Claim 16 wherein the curing of step (b) is facilitated by adding a co-initiator compound to
25 the gel coat composition.


19 - The process of Claim 18 wherein the co-initiator compound is t-butyl peroctoate.

20 - The process of claim 18 wherein the co-initiator compound is 2,5-dimethyl-2,5-di(2,5-
30 diethylhexanoyl peroxy)hexane.

21 - The gel coated article obtained by the process of Claim 16.

1/1

Figure 1



INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 97/06017

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C08F8/14 C09D133/14

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 273 795 A (SOC. CHIM. DES CHARBONNAGES S.A.) 6 July 1988 see claim 1: examples 9.10 ---	1-8
A	US 4 177 338 A (A. VRANCKEN) 4 December 1979 cited in the application -----	



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

12 March 1998

Date of mailing of the international search report

23/03/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040. Tx. 31 651 200 nl.
Fax: (+31-70) 340-3016

Authorized officer

Cauwenberg, C

INTERNATIONAL SEARCH REPORT

Information on patent family members

In: International Application No

PCT/EP 97/06017

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 273795 A	06-07-88	FR 2607509 A	03-06-88
		FR 2615517 A	25-11-88
		JP 63179912 A	23-07-88
<hr/>			
US 4177338 A	04-12-79	GB 1410697 A	22-10-75
		AT 333508 B	25-11-76
		BE 821408 A	24-04-75
		BR 7408883 A	04-05-76
		CA 1029894 A	18-04-78
		CH 620934 A	31-12-80
		DD 120031 A	20-05-76
		DE 2450621 A	30-04-75
		DK 556074 A	16-06-75
		FR 2249098 A	23-05-75
		JP 50083494 A	05-07-75
		LU 71185 A	24-06-75
		NL 7413862 A	29-04-75
		US 4312726 A	26-01-82
<hr/>			